



**ELECTROTECHNICAL TESTING INSTITUTE**  
**Pod Lisem 129**  
**171 02 Praha 8 - Troja**  
**Notified Testing laboratory No. 1014**  
**No. of the Test Report: 701952-01/02**

No. of pages: 4  
No. of annexes/No. of an. pages: 0/0

Issued: 22. 6. 2017



## TEST REPORT FOR REACTION TO FIRE

**Name of product:** Cables  
**Type of product:** NYY-J  
**Ratings:** NYY-J 3x2,5 mm<sup>2</sup> E<sub>ca</sub>  
NYY-J 5x2,5 mm<sup>2</sup> E<sub>ca</sub>  
**Part number:** -  
**Manufacturer:** SC Omnicable SRL, str. Principala 175B ,  
Ernei, Mures, Romania  
**Production site:** same as manufacturer  
**Ordering firm:** SC Omnicable SRL, str. Principala 175B ,  
Ernei, Mures, Romania  
**Number of tested samples:** 2  
**Samples submitted on:** 8. 6. 2017  
**Location of testing:** EZÚ  
**Tested from** 20. 6. 2017 **through** 20. 6. 2017  
**Other data:** -  
**The product was tested according to:** EN 60332-1-1:04+A1:15,  
EN 60332-1-2:04+A1:15+A11:16

Compiled by: **Břetislav Dušek**



Approved by: **Jan Tůma**  
Testing laboratory technical manager

Test results stated in the test report apply only to the tested subject and unless specified otherwise in the test report, the tests were performed using the method and under the conditions determined in the test regulations, technical norm, instructions for use and information provided by the manufacturer on the tested subject and using accessories required by the manufacturer.  
Without written consent, this report must not be reproduced in any other way than as a whole.  
When referring to services of EZÚ, s. p., as an accredited laboratory, the customer specified in this report must use the following formulation:  
"Tested by test laboratory no. 1056, accredited by CAI".

Phone: +420 266 104 111

Fax: +420 284 680 070

www.ezu.cz

Test	Prescribed			Observed
<b>Test on complete cable</b>				
<b>NYY-J 3x2,5 mm<sup>2</sup></b>				
Test for vertical flame propagation EN 60332-1-2, article 5 EN 60332-1-2, article 6				
- outer diameter		[mm]		10,5
- flame application time		[s]	60	60
- not damage area from lower edge of the top support	min.	[mm]	50	346
- damage area from lower edge of the top support	max.	[mm]	540	487
- flame spread H	≤	[mm]	425	141

Test type: **Classification of electric cables according to reaction to fire**

Standard: EN 50575, EN 13501-6,

EN 60332-1-2, EN 60332-1-1

Test of vertical flame spread on a single cable

Cable type: **NYY-J 3x2,5 mm<sup>2</sup>**

Cable producer: SC Omnicable SRL

date of test: 20. 6. 2017

Classification according to EN 13501-6: **E<sub>ca</sub>**


**EN 60332-1-2**



**Before test**



**Course of the tests**



**After test**

Test	Prescribed			Observed
<b>Test on complete cable</b>				
<b>NYY-J 5x2,5 mm<sup>2</sup></b>				
Test for vertical flame propagation EN 60332-1-2, article 5 EN 60332-1-2, article 6				
- outer diameter		[mm]		12,7
- flame application time		[s]	60	60
- not damage area from lower edge of the top support	min.	[mm]	50	352
- damage area from lower edge of the top support	max.	[mm]	540	481
- flame spread H	≤	[mm]	425	129

Test type: **Classification of electric cables according to reaction to fire**

Standard: EN 50575, EN 13501-6,

EN 60332-1-2, EN 60332-1-1

Test of vertical flame spread on a single cable

Cable type: **NYY-J 5x2,5 mm<sup>2</sup>**

Cable producer: SC Omnicable SRL

date of test: 20. 6. 2017

Classification according to EN 13501-6:

E<sub>ca</sub>

**EN 60332-1-2**



**Before test**



**Course of the tests**



**After test**

**Measuring and testing equipment**

Used	Prescribed	Observed
X	Metter 100 cm	N 400013
X	Slide caliper	259
X	Table stopwatch	551705
X	Test under fire conditions	20 780

If an uncertainty of measurement is given, the expanded a measurement uncertainty is the product of the standard measurement uncertainty and coverage factor  $k = 2$ , which corresponds to a coverage probability of approximately 95% in a normal distribution.

Laboratory conditions during the test were in accordance with specifications of the standards listed on the first page of this test report.

Compiled by: **Břetislav Dušek**

